

TECHNICAL DATASHEET



Article: Style 442
Setting (Thr/cm): 4,0/4,0
Weave: Twill 2/2
Finish: loomstate

| <u>Construction:</u> | Warp | Weft |
|-------------------------------|-----------|-----------|
| Yarn material ¹⁾ : | Carbon 3K | Carbon 3K |
| Yarn number ¹⁾ : | 200 tex | 200 tex |

| <u>Technical Data:</u> | | Unit | Target | +/- | Tolerance |
|--------------------------------|------|-------------------|------------|-----|-----------|
| Fibre density ^{1) 3)} | Warp | g/cm ³ | n.G. | +/- | n.G. |
| | Weft | g/cm ³ | n.G. | +/- | n.G. |
| Linear density ¹⁾ | Warp | tex | 200 | +/- | 10 |
| | Weft | tex | 200 | +/- | 10 |
| Twist ¹⁾ | Warp | T/m | | +/- | |
| | Weft | T/m | | +/- | |
| Setting | Warp | Thr./cm | 4,0 | +/- | 0,2 |
| | Weft | Thr./cm | 4,0 | +/- | 0,2 |
| Weave | | | Twill 2/2 | | |
| Weight | | g/m ² | 160 | +/- | 5 |
| Dry weight | | g/m ² | 160 | +/- | 5 |
| Moisture content | | % | 0,5 | +/- | max. |
| Thickness ²⁾ | | mm | 0,30 | +/- | 0,05 |
| Width | | cm | as ordered | +/- | 1 |
| | | | | | |

¹⁾ = n.G. = depending on order and yarn specification

³⁾ = no measure, certified by supplier

²⁾ = approximate value, not for release

Remarks:

| | | |
|-------------------------------|----------------------------------|--|
| Date 11.08.2009 | Q.A. Monika Dassel | This Datasheet does not include Revision Service. |
|-------------------------------|----------------------------------|--|